

**100% COTTON HANK MULTI PLY YARN**

Nominal Count	<b>2/6<sup>s</sup> OE</b>	<b>3/6<sup>s</sup> OE</b>	<b>4/6<sup>s</sup> OE</b>	<b>6/6<sup>s</sup> OE</b>
Actual Count	2.8	1.8	1.3	0.9
<b>CSP</b>	<b>1400</b>	<b>1450</b>	<b>1470</b>	<b>1530</b>
Single Yarn Strength in Kg	1.4	2.5	3.8	5.8
Nominal TPI	10.3	10.3	7.8	6.0

Nominal Count	<b>2/8<sup>s</sup> OE</b>	<b>3/8<sup>s</sup> OE</b>	<b>4/8<sup>s</sup> OE</b>	<b>5/8<sup>s</sup> OE</b>
Actual Count	3.8	2.4	1.8	1.5
<b>CSP</b>	<b>1400</b>	<b>1450</b>	<b>1450</b>	<b>1500</b>
Single Yarn Strength in Kg	1.2	2.2	2.9	3.4
Nominal TPI	12.6	11.3	10.3	8.1

Nominal Count	<b>2/10 KW GM</b>	<b>2/10 KW BM</b>	<b>4/10 KW</b>	<b>4/10 KW GM</b>
Actual Count	4.5	4.5	2.2	2.2
<b>CSP</b>	<b>2950</b>	<b>2300</b>	<b>2800</b>	<b>3000</b>
Single Yarn Strength in Kg	3.8	3.1	6.1	6.4
Nominal TPI	12.5	12.5	4.5	4.5

Nominal Count	<b>2/26 KW SM</b>	<b>2/26 KW BM</b>	<b>2/26 KW OB</b>	<b>3/26 KW SM</b>
Actual Count	12.5	12.8	12.8	8.2
<b>CSP</b>	<b>2350</b>	<b>2380</b>	<b>2250</b>	<b>2600</b>
Single Yarn Strength in Kg	1.7	1.8	1.6	2.3
Nominal TPI	21.8	21.8	21.8	15.8

- \* OB=Only Bleached
- \* BM=Bleached Mercerised
- \* GM=Grey Mercerised
- \* SM=Scoured Mercerised